

SPECIFICATION

(承认书)

NO:

CUSTOMER 客户			
BFN PART NO. 博富能产品编号	H1000 7/5AAA		
TYPE 类型	1.2V 1000mAh 7/5AAA Ni-MH Cylindrical battery cell 1.2V 1000mAh 7/5AAA 镍氢圆柱型充电电池		
DATE SUBMITTED 呈交日期			
RENARK 备注			
APPROVAL SIGNATURE & CHOP 核准签章			

深圳市博富能电池有限公司

SHENZHEN BOFUNENG BATTERY CO.,LTD

地址 Add: 深圳市龙岗区龙城街道五联社区朱古石路春洋工业园 A、E 栋

A&E Building, Chun Yang Industrial Park, Zhu Gu Shi Road, Wu Lian Community, Long Cheng Street, Long Gang District, Shen Zhen, China

邮编 P.C: 518172

电话 TEL: 0755-84642975 89312858

传真 Fax: 0755 84642732

网址 http: //www.bfnbattery.com

E-mail:bfn@bfnbattery.com

1. 参数规格 SPECIFICATIONS:

APPROVED BY 批准	CHECKED BY 核查	PREPARED BY 准备

本公司保留更改规格书资料的权力, 不另行通知。

Subject to be modified without prior notice



单体电池类型	密封圆型低自放电镍氢电池
Type	Sealed Ni-MH Cylindrical Battery cell
型号	H1000 7/5AAA
Size	
尺寸	7/5AAA (HR10.5/67.0)
Model	
标称电压	1.2V
Nominal Voltage	
标称容量(20°C, 标准充电, 0.2CA 放电至 1.0V)	1000mAh
Nominal Capacity (20°C, Standard Charge, 0.2CA discharge to 1.0V)	
典型容量	1000mAh
Typical Capacity	
最小容量	970mAh
Minimum Capacity	
平均重量(约)	18.5g
Typical Internal Impedance(at 1 kHz)	
内阻	≤35mΩ
Internal Impedance At 1000 Hz	(充电后 After Charge)
电池尺寸(包括 PVC 管)	
Dimensions(including PVC tube)	
直径 Diameter (D)	Max: 10.5mm
高度 Height (H)	Max: 67.0mm
充电方法(20°C)	
Charging Method: (20°C)	
标准充电	0.1CA(100mA)充电 14~16 小时
Standard Charge:	Charge with 0.1CA (100mA) for 14~16 h
快速充电	0.3CA(300mA)充电 4.5 小时
Quick Charge	Charge with 0.3CA(300mA) for 4.5 h
急速充电	0.5CA(500mA)充电 2.2 小时, -Δ=10mV 控制
Fast Charge:	Charge with 0.5CA(500mA) for 2.2 h (Under -ΔV=10mV)
最大过充电电流	0.1CA(100mA) 时间不大于 100 小时
Max Overcharge Current	0.1CA(100mA)charge(No longer than 100 h)
微电流充电电流	30~50mA
Trickle Current	
使用温度(参考)	
Operating Temperature(reference only):	
存放	-20°C~+35°C
Storage	
放电	-20°C~+60°C
Discharge	
标准充电	0°C~+45°C
Standard Charge	
快速充电	+10°C~+45°C
Fast Charge	



2. 性能测试 Performance:

测试项目 Testing Item	测试条件 Testing Conditions	要求 Standard
标准测试条件 Standard Testing Condition	以下测试如未特别规定, 均应在 20±5℃, 相对湿度 65±20% 条件下进行。电压表、电流表的精度±1%。 If not specially described, Temperature 20℃±5℃ Relative Humidity: 65±20%。Parapet measuring instruments: ±1% for voltage/current/capacity; ±2℃ for temperature; ±0.1% for time.	
(1) 标准充电 Standard Charge	以 0.2CA 放电至 1.0V, 再以 0.1CA 恒流充电 14~16 小时。 0.2CA discharge to 1.0V, then 0.1CA charge for 14~16h (Constant Current)	
(2) 急速充电 Fast Charge	以 0.2CA 放电至 1.0V, 再以 0.5CA 的电流恒流充电 2.2 小时, -ΔV=10mV 控制。 0.2CA discharge to 1.0V, then 0.5CA charge for 2.2 h (Under -ΔV controlled 10mV)	
(3) 开路电压 Open Circuit Voltage	标准充电后, 14 天内进行测试。 test within 14 days after standard charge	≥1.25V
(4) 额定容量 Nominal Capacity	标准充电, 搁置 1~4 小时, 0.2CA 放电至 1.0V, 允许循环三次。 Have 1-4 h of rest after standard charge, then 0.2CA discharge to 1.0V, 3 cycles permitted	≥300 分钟 ≥300 min
(5) 高倍率放电容量 High Rate Discharging Capacity	快速充电, 搁置 1~4 小时, 0.5CA 放电至 1.0V, 允许循环三次。 Have 1-4 h of rest after fast charge, Then 0.5CA discharge to 1.0V, 3 cycles permitted	≥108 分钟 ≥108 min
(6) 循环寿命 Cycle Life	按 GB/T 22804.2-2008/IEC61951-2: 2003(7.4.1.1) ※for GB/T 22804.2-2008/IEC61951-2: 2003(7.4.1.1)	≥500 次 ≥500 cycles
(7) 过充特性 Overcharge	按 (4) 额定容量测试后, 0.1CA 充电 48 小时, 检查电池外观, 0.2CA 放电至 1.0V; After (4) testing, The cell shall be charge, in an ambient temperature of 20℃±5℃, at a constant current of 0.1CA for 48 h, After this charging operation, the cell shall be stored, in an ambient temperature of 20℃±5℃, for not less than 1 h and not more than 4 h. The cell shall then be discharge, at 20℃±5℃ at a constant current of 0.2CA to a final voltage of 1.0V	无变形、无漏液 ≥270 分钟 ≥270 min
(8) 安全性能(过放电) Over-Discharge Safety device operation	以 0.2CA 强制放电至 0V, 然后将电流增至 1.0CA 放电 60 分钟。 The cell shall undergo a forced discharge in an ambient temperature 20℃±5℃, at a constant current of 0.2CA, to a final voltage of 0V. The current shall then be increased to 1.0CA and the forced discharge continued in the same ambient temperature of 20℃±5℃, for 60min.	电池不爆炸, 但允许有漏液或变形。 The cell shall not disrupt or burst, Leakage of electrolyte and deformation of the cell are acceptable



<p>(9)温度 Temperature</p>	<p>电池在 20±5℃下按 (2) 快速充电后, 在下面温度下存放 3 小时, 0.5CA 放电至 1.0V。 a) 放电温度: 0℃ b) 放电温度: 20℃ c) 放电温度: 40℃ Fast charged as (2) under 20±5℃, stored 3 h under following temperatures, then 0.5CA discharge to 1.0V: a) Discharging Temperature: 0℃ b) Discharging Temperature: 20℃ c) Discharging Temperature: 40℃</p>	<p>放电时间 ≥ 100 分钟 ≥ 108 分钟 ≥ 90 分钟 Discharging Time ≥ 100 min ≥ 108 min ≥ 90min</p>
<p>(10)荷电保持能力(自放电) Charge(capacity) retention(Self-discharge)</p>	<p>电池在标准充电后, 在 20±5℃, 开路存放 28 天。0.2CA 放电至 1.0V。 After standard charge, stored for 28 days under 20±5℃, then 0.2CA discharged to 1.0V</p>	<p>放电时间 ≥180 分钟 Discharging Time ≥180min</p>
<p>(11)贮存 Storage</p>	<p>电池以 (1) 标准充电中规定的充电态, 在 20±5℃及相对湿度 65±20%的条件下, 开路存放 6 个月, 按 (4) 进行额定容量测试。 Standard Charged as (1) condition and stored for 6 months under 20℃±5℃, then tested as (4) condition</p>	<p>放电时间 ≥240 分钟 无变形, 漏液 Discharging Time ≥240 min</p>
<p>(12)抗震性、跌落 Mechanical test: bump test、Free falling(drop)</p>	<p>1) 跌落试验: 电池自 100cm 高度自由落体至 10mm 硬质木板上, 任意方向自由跌落 3 次 The battery shall be subjected to drop from the height of 1 m to an oak board more than 1 cm thick, the test should be carried for 3 times at each direction of the battery axis. 2) 抗震条件: 震幅 4mm, 频率 1000 次/分钟, 任意方向震动 60 分钟 The ability of the cell to withstand mechanical Shock shall be checked by means of bump test carried out in accordance with IEC 60068-2-29. After standard charge, The bump test shall be changed carried out in an ambient temperature of 20±5℃, under the following conditions: -peak acceleration(A) 98m/s² (10gn) -corresponding duration to pulse(D) 16ms -corresponding velocity charge 1,00ms -number of bumps 1000±10 When the bump test has been completed, each cell shall be stored for not less then 1 h and mot more then 4 h in an ambient temperature of 20℃±5℃, It shall then be discharge in the same ambient temperature with a constant current of 0.2CA to a final voltage of 3.0V</p>	<p>电池保持电气性能, 允许有机械变形或损伤 The battery maintains the electrical specification, the mechanical distort or damage is permitted</p>



3.外观 Appearance:

3.1 电应无裂痕、断口、灰尘、变色、漏液及变形。

The battery should not have the fissure, the fracture, the dust, the color deterioration, to leak the fluid and the distortion.

4.注意事项 note:

4.1 请勿将电池投入火中及试图拆开;

Do not dispose of cell into fire or be dismantled under any condition.

4.2 请勿与其它种类电池或旧电池混合使用;

Do not mix different cell types and capacities in the same battery assembly.

4.3 请勿超过博富能规格书电流充放电。

Charge and discharge under specified ambient temperature recommended to BFN specification.

4.4 请勿将电池短路, 以免电池永久性损坏;

Short circuit leading to cell venting must be avoided .

4.5 请勿直接焊接电池以免损坏密封圈及安全伐;

Never solder onto cell directly.

4.6 请勿将电池的正、负反接, 以免电池过充电或过放电而损坏;

Cell reversal should be avoided.

4.7 如果电池在极限条件下使用, 可能会减短电池使用寿命,如: 极限温度、深度循环、极度过充电及过放电;

Use batteries in extreme condition may affect the service life, such as: extreme temperature, deep cycle, extreme overcharge and over discharge.

4.8 电池应于储存在阴冷干燥环境中;

Batteries should be stored in a cool dry place.

4.9 电池在使用时发现异常或问题, 立即停止使用, 联络当地电池经销商处理;

Once problems be found, stop using, send batteries to local dealer.

5.贮存 Storage

5.1 保证电池维持容量水平, 建议镍氢电池及电池组在-20~25℃、低温度、无腐蚀剂气体条件下贮存
It is strongly recommended to store Ni-MH batteries and cells in the temperature range from -20 to 25℃ ,and in low humidity and no corrosive gas environment, to maintain a reasonably high capacity recovery level.

5.2 镍氢电池避免在较高温度或较高湿度下贮存, 否则将导致电池漏液、生锈, 以及容量降低。

Avoid storage higher (e.g.35℃),lower temperature than -20℃ ,or higher humidity which would result in deterioration or damage to the cells and batteries such as follows:

5.3 长期存放将可能导致镍氢电池及电池组容量降低, 并需 1~3 个充电/放电循环后才能达到最高放电容量。

Up to three full cycles of charge /discharge after long-termed storage may need to obtain highest capacity.

7. 保质期限: 12 个月。

Quality assurance period:12 months.



※ GB/T 22084.2-2008/IEC61951-2: 2003(7.4.1.1)循环寿命测试方法:

循环数	充电	充电状态下静置	放电
1	0.1CA(100mA)14~16 小时	无	0.25CA(250mA)2 小时 20 分
2-48	0.25CA(250mA)3 小时 10 分钟	无	0.25CA(250mA)2 小时 20 分
4	0.25CA(250mA)3 小时 10 分钟	无	0.25CA(250mA)到 1.0V
50	0.1CA(100mA)14~16 小时	1-4 小时	0.2CA(200mA)到 1.0V

- 1) 每两个 50 次循环之间间隔时间不大于 14 天, 以相同的顺序进行第 50、100、150、200、250、300、350、400、及 450 次循环。
- 2) 测试过程中电池放电电压, 下降到 1.0V 时, 停止放电。
- 3) 当第 50 次循环的放电持续时间达不到 3 小时 (额定容量的 60%) 时, 用 0.1CA(100mA) 充电 16 小时, 0.2CA(200mA) 放电至 1.0V, 然后循环 3 次合格后再进行下一个 50 次循环。


※for GB/T 22084.2-2008/IEC61951-2: 2003(7.4.1.1) Endurance in cycles

Cycle number	Charge	Stand in charged condition	Discharge
1	0.1CA (100mA) for 14~16h	none	0.25CA (250mA) for 2h 20 min
2-48	0.25CA (250mA) for 3h 10 min	none	0.25CA (250mA) for 2h 20 min
49	0.25CA (250mA) for 3h 10 min	none	0.25CA (250mA) to 1.0 V
50	0.1CA (100mA) for 16h	1 h to 4 h	0.2CA (200mA) to 1.0 V


- 1 The interval time between every 50 cycles is less than 14 days, with the same way to do the 50th, 100th, 150th, 200th, 250th, 300th, 350th, 400th and 450th cycles
2. Stop discharging once the voltage is down to 1.0V on the testing procedure of discharge voltage.
- 3.If the discharge time of the 50 cycles can not reach 3 hours(60% of the nominal capacity), charge with current 0.1CA(100mA) for 16 hours, then discharge with 0.2CA(200mA) to 1.0V, if the first three cycles pass, then continue the next 50 cycles.

电池外形图 Battery appearance graph:


Standard charge characteristics



Rapid charge characteristics



Discharge characteristics at various rate



以上为单体电池充放电曲线。

The above is single battery charging and discharging curve